

**DESCRIPTION**

Microlite® FSK Formaldehyde-free™ duct wrap insulation is a lightweight, highly resilient, blanket-type thermal insulation. The insulation blanket is manufactured from rotary-process fiberglass bonded with a formaldehyde-free resin.

**AVAILABLE FORMS**

Microlite Formaldehyde-free™ insulation is available in a variety of densities, thicknesses and roll lengths. It is supplied with an FSK (foil-scrim-kraft) vapor barrier facing to meet installed performance requirements, with a 2" (51 mm) stapling tab.

**USES**

Microlite insulation is recommended as thermal insulation for the exterior of HVAC systems or other spaces or surfaces where temperature control is required.

**LIMITATION**

Microlite FSK duct wrap is not recommended for use on duct systems in service at temperatures above 250°F (121°C). It should not be used in weather-exposed applications without proper protection.

**STORAGE**

Microlite FSK duct wrap should be kept clean and dry during storage, transport, installation, and system operation.

**FACING INFORMATION**

FSK Aluminum Foil

Reinforced with fiber glass scrim laminated to UL-rated kraft.

Permeance: 0.02 perms\*

\*Per ASTM E96, Procedure A for facing material prior to lamination. After lamination, permeance values may be higher.

**GENERAL PROPERTIES**

Temperature (max.) – ASTM C411	250°F (121°C)
Water vapor sorption – ASTM C1104	<5% by weight
Corrosivity with steel – ASTM C665	Does not accelerate
Fungi resistance – ASTM C1338	Does not breed or promote

**STANDARD THICKNESSES AND PACKAGING**

Type	100' Roll (31 m)	75' Roll (23 m)	50' Roll (15 m)
75	1 (25)*, 1½ (38)	2 (51), 2 ½ (56)	3 (76), 4 ½ (112)
100	1½ (38)	2 (51)	–
150	–	1½ (38)	2 (51)

\*1" for Canadian use only

Note: Additional thicknesses, widths and other lengths available on special order. Contact Regional Sales Office for availability.



Color of product will differ depending on manufacturing location.

**SURFACE BURNING CHARACTERISTICS**

Microlite insulation meets the Surface Burning Characteristics and Limited Combustibility of the following standards:

Standard/Test Method

- ASTM E84
- UL 723
- NFPA 90A and 90B
- UL Guide No. 40 U8.3. Card R3711
- CAN/ULC S102

Maximum Flame Spread Index	25
Maximum Smoke Developed Index	50

Note: Faced materials are tested as composite products (insulation, adhesive and facing).

**SPECIFICATION COMPLIANCE**

ASTM C1290	Type 75, 100, & 150
ASTM C553*	
Type I, Type II	Type 75 & 100
Type I, Type II, Type III	Type 150
*For faced material: 250°F (121°C) maximum temperature.	
ASTM C1136s†	
Type II	FSK Facing
†Replaces HH-B-100B, Type II.	
Canada: CGSB 51-GP-11M	
NYC MEA 40-75-M	

**CERTIFIED JM FORMALDEHYDE-FREE™ FIBERGLASS INSULATION**

Certified JM Formaldehyde-free™ fiber glass insulation offers superior thermal and acoustical performance—and it improves indoor air quality because it's made without formaldehyde. Why is that important? Because the U.S. Environmental Protection Agency (EPA) recommends limiting exposure to formaldehyde as much as possible, and the California Air Resources Board, a division of the California EPA, recommends that builders and architects use building materials and insulation made without formaldehyde.



### APPLICATION RECOMMENDATIONS


The R-value will vary depending upon how much the insulation is compressed during installation. To obtain the published installed R-values, the insulation stretch-out should be determined using the following table:

#### Duct Wrap Stretch-outs

Labeled Thick. (in)	Installed Compressed			
	Thickness (in)	Round	Square	Rectangular
1	0.75	P+ 7.0"	P+ 6.0"	P+ 5.0"
1½	1.125	P+ 9.5"	P+ 8.0"	P+ 7.0"
2	1.50	P+ 12.0"	P+ 10.0"	P+ 8.0"
2 ½	1.65	P+ 13.0"	P+ 11.0"	P+ 8.5"
3	2.25	P+ 17.0"	P+ 14.5"	P+ 11.5"
4 ⅔	3.30	P+ 24.5"	P+ 21.0"	P+ 19.0"

Stretch-outs include 2" (51 mm) for overlap. P = perimeter of duct to be insulated.

Prepare overlap by removing approximately 2" (51 mm) of insulation from facing.



### THERMAL CONDUCTIVITY (ASTM C518)

Type	k*		k	
	Compressed Thickness		Labeled Thickness	
	Btu•in/(hr•ft²•°F)	W/m•°C	Btu•in/(hr•ft²•°F)	W/m•°C
75	0.27	0.039	0.29	0.042
100	0.25	0.036	0.27	0.039
150	0.24	0.035	0.25	0.036

Conductivity at 75°F (24°C) mean temperature.

\*Tested with material thickness compressed 25%.

Before applying duct wrap, sheet metal duct shall be clean, dry and tightly sealed at all joints and seams.

Wrap insulation around duct with facing to the outside so the 2" (51 mm) flap completely overlaps facing and insulation at the other end of stretch-out. Insulation shall be snugly butted.

Secure seams with outward clinching staples placed approximately 6" (152 mm) on center. If required, seal seam with pressure-sensitive tape designed for use with duct insulation. Insulation on the underside of ducts spanning 24" (610 mm) or greater shall be secured with mechanical fasteners and speed clips spaced approximately 18" (457 mm) on center. Fasteners should be cut off flush after the speed clips are installed, and when required, sealed with the same tape as specified above.

Adjacent sections of duct wrap insulation shall be snugly butted with the circumferential 2" (51 mm) tape flap overlapping and secured as recommended for the longitudinal seam. When a vapor seal is required, two coats of vapor retarder mastic reinforced with one layer of 4" (102 mm) wide, open-weave glass fabric may be used in lieu of pressure-sensitive tape.

### GUIDE SPECIFICATIONS

**Insulation for Metal Ducts.** All ducts shall be insulated on the outside with a Formaldehyde-free™, flexible glass fiber blanket. Microlite Formaldehyde-free™ fiber glass duct wrap insulation should have a minimum installed R-value\* of \_\_\_\_\_, and a Type \_\_\_\_\_ facing. Insulation shall be furnished with a factory-applied facing with a composite UL FHC rating of 25/50.

\*The minimum insulation installed R-value should be determined in accordance to the duct operating and ambient conditions.

### INSTALLED R-VALUES

Type	Labeled Thickness		Installed "R"***		Out-of-Package "R"	
	in	mm	(hr•ft²•°F)/Btu	m²•°C/W	(hr•ft²•°F)/Btu	m²•°C/W
<b>Type 75 - 0.75 pcf (12kg/m³)</b>						
75	1	25	3.0	0.53	3.8	.67
	1½	38	4.2	0.74	5.2	0.92
	2	51	5.6	0.99	6.9	1.22
	2 ½	56	6.0	1.08	7.5	1.33
	3	76	8.3	1.46	10.3	1.81
	4 ⅔	112	12.0	2.16	15.0	2.66
<b>Type 100 - 1.00 pcf (16kg/m³)</b>						
100	1½	38	4.5	0.79	5.6	0.99
	2	51	6.0	1.06	7.4	1.30
<b>Type 150 - 1.5 pcf (24kg/m³)</b>						
150	1½	38	4.7	0.83	6.0	1.06
	2	51	6.3	1.11	8.0	1.41

\*\*\*Installed R-value calculated with a material thickness compressed to a maximum of 25% following recommended duct wrap stretch-outs.